



AWNMAX[®]


antiwicking scrim, hard acrylic topcoat.




1153 MED. BLUE



1150 DK. BLUE



8102 SULTAN BLUE



6111 ROYAL BLUE




8101 NAVY BLUE



1162 CREAM




1170 IVORY



4144 TEAL



1142 DK. GREEN




6107 FOREST GREEN



*1160 COOL WHITE



1171 TAN




8103 SAND




1132 YELLOW




1181 GOLD




6102 GREY




3180 BLACK



6105 CORPORATE RED



8104 CARDINAL RED



6103 BURGUNDY

- Proven durability and performance with 20 years trouble-free track record
- Unparalleled translucent quality, not just brighter but better quality illumination
- Flame retardant meets C.S.F.M., NFPA 701, CAN/ULCS109M, UL 214
- Exceedingly strong knitted polyester scrim
- Unrivalled dye lot consistency - production after production color consistency
- Patented hard acrylic topcoat provides superior cleanability, resists marking and bruising
- Super smooth top surface stays clean longer, easier to clean
- Accepts 3M Scotchcal translucent films for graphic decoration
- Weldable
- 10 year warranty

	STANDARD	METRIC (W/F)		ENGLISH (W/F)	
Width × Length	ASTM D-751	203.5cm × 29m		80.1 inch × 32 yds	
Weight	ASTM D-751	630	g / m ² *	19	oz / yd ² *
Thickness	ASTM D-751	0.51	mm *	20	mil *
Tesile Strength (Strip)	ASTM D-751	1,870 / 1,530	N/5cm	214 / 175	Lbs / inch
Breaking Elongation	ASTM D-751	25 / 26	%	25 / 26	%
Tear Strength (Trapezoid)	ASTM D-751	215 / 170	N	48 / 38	N

* Color # 1160 (Cool White) = UL Standard : Weight 680 g / m² (20 oz / yd²) , Thickness 0.53 mm (21 mil)



Manufactured by

HIRAOKA & CO., LTD.
 Tokyo, Japan
 Hira1902@tarpo-hiraoka.com
 www.tarpo-hiraoka.com